



**BRADY B-508 BRADYTAG® COMPUTER PRINTABLE TAG**

TDS No. B-508  
Effective Date: 06/02/2017

**Description:**

**GENERAL**

**Print Technology:** Dot Matrix or Thermal Transfer  
**Materials Type:** Nomex® Tag  
**Available Colors:** White and Yellow

**APPLICATIONS**

Designed as a high performance wire bundle and cable identification tag for use in harsh environments.

**RECOMMENDED RIBBONS**

**Dot Matrix**

Brady Series R2000  
Brady Series R5000

**Thermal Transfer**

Brady Series R4300

**REGULATORY/AGENCY APPROVALS**

Brady B-508 is RoHS compliant to 2005/618/EC MCV amendment to RoHS Directive 2002/95/EC.

**SPECIAL FEATURES**

B-508 has excellent tear, solvent, and heat resistance properties.

The service temperature range is -70°C (-94°F) to +130°C (266°F)

**Details:**

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000	0.012 inch (0.305mm)
Hole Tear Strength	LTP 1412* - Machine -Cross	16 lb (7.3 kg) 21 lb (9.5 kg)
Tensile Strength and Elongation	ASTM D 1000 -Machine direction	191 lbs/inch (3.4 kg/mm), 22%
Dielectric Strength	ASTM D 1000	14,000 Volts

Vacuum Outgassing Tested at an outside laboratory Test samples printed with R4300 Series ribbon	ASTM E595 Specification Limits % Total Mass Loss (TML) - 1.0% maximum % Collected Volatile Condensable Material (CVCM) -0.10 maximum % Water Vapor Recovered - Report	<i>White/R4300:</i> % TML - 1.53 % CVCM - 0.10 % WVR - 1.13 <i>Yellow/R4300:</i> % TML - 1.7 % CVCM - 0.10 % WVR - 1.45
Surface Flammability of Materials Using a Radiant Heat Energy Source Tested at an outside laboratory Test samples printed with R4300 Series ribbon	ASTM E162 Common Maximum - 35	Flame Spread Index (Is) (rounded average result of 4 tests) White/R4300 - 15 Yellow/R4300 - 15
Specific Optical Density of Smoke (Ds) Tested at an outside laboratory Test samples printed with R4300 Series ribbon	ASTM E662 Common Maximum Flaming Mode at 1.5 minutes - 100 Flaming Mode at 4.0 minutes - 200	Specific Optical Density (Ds) (average of 3 tests) <i>White/R4300:</i> Flaming Mode at 1.5 minutes - 14 Flaming Mode at 4.0 minutes - 54 Non-Flaming Mode at 1.5 minutes - 1 Non-Flaming Mode at 4.0 minutes - 3 <i>Yellow/R4300:</i> Flaming Mode at 1.5 minutes - 24 Flaming Mode at 4.0 minutes - 48 Non-Flaming Mode at 1.5 minutes - 6 Non-Flaming Mode at 4.0 minutes - 9

\* Brady Corporation Lab Test Procedure

Performance properties tested on B-508 printed with Series R200 and R500 dot matrix ribbons and with Series R4300 thermal transfer ribbon. B-508 printed samples were tested on white and yellow topcoats. Unless noted, results are the same for both colors of topcoat and all ribbons.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
Long Term High Service Temperature	30 days at 266°F (130°C)	Slight discoloring on face and moderate discoloration on back of tag. No visible effect to print.
Long Term High Service Temperature	30 days at 302°F (150°C)	White tag exhibits slight discoloration on face and back of tag. Yellow tag exhibits severe fade in that yellow color has almost disappeared. Tag exhibits slight fading of the yellow color after 14 days at 150°C. Print is legible on all tag colors.
Short Term Service Temperature	7 days at 175°C	White tag exhibits moderate discoloration on the face and back of the tag. Yellow tag exhibits severe fade in that the yellow color has disappeared. Print is legible on all tag colors.
Short Term Service Temperature	30 minutes at 356°F (180°C)	Slight discoloration and slight warping of tag. No visible effect to print.

Low Service Temperature	30 days at -94°F (-70°C)	No visible effect
Humidity Resistance	30 days at 100°F, 95% R.H.	No visible effect
UV Light Resistance	30 days in UV Sunlighter™ 100	Very slight discoloration to white topcoat. No effect to yellow topcoat. Slight discoloration on back of tag. Slight R5000 print fade. No visible effect to R2000 or R4300 print.
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherometer	Slight print fade with R2000 and R5000. No visible effect to R4300 print.
Salt Fog Resistance	ASTM B 117	No visible effect
Print Adherence per SAE-AS81531 (Sec 3.4.2)	SAE-AS81531 (Sec 4.6.2) 20 eraser rubs with hard hand pressure	Pass - Print still legible with all ribbons
Solvent Resistance per SAE-AS81531 (Sec 3.4.3) Solution A Solution C Solution D JP-8 Jet Fuel**	MIL-STD-202, Method 215K 3 cycles of 3 minute immersions in specified fluids followed by toothbrush rub after each immersion	Pass - Print still legible with all ribbons in all test fluids

Solution A: 1 part isopropyl alcohol, 3 parts mineral spirits

Solution B: deleted from MIL-STD-202, Method 215K

Solution C: BIOACT EC-7R terpene defluxer

Solution D: 42 parts water, 1 part propylene glycol monomethyl ether, 1 part monoethanolamine at 70°C

\*\* JP-8 is an additional chemical tested; it is not specified in MIL-STD-202, Method 215K

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
----------------------	---------------------

B-508 samples printed with Series R5000 and R2000 dot matrix ribbons with Series R4300 thermal transfer ribbons. Samples dwelled a minimum of 24 hours before testing. Test conducted at room temperature on B-508 white and yellow. Testing consisted of 30 minute fluid immersion. After immersion, the printed image was rubbed on 10 times with a cotton swab saturated with the test fluid. The rating scale below shows the effect to the quality of the print and topcoat, if applicable, for each sample. Unless noted, results are the same for the white and yellow topcoats.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	WITHOUT RUB	DOT MATRIX WITH RUB R2000 and R5000	THERMAL TRANSFER WITH RUB R4300
Methyl Ethyl Ketone	White - 2 print and topcoat Yellow - 2 print, 3 topcoat	5	5
Propylene Glycol	1	1	1
5% Salt Solution	1	1	1

Isopropyl Alcohol	1	1	2
JP-8 Jet Fuel	1	1	2
Mil 5606 Oil	1, tag slightly stained red	1	2
Gasoline	1	1	3
Skydrol® 500B-4	1	2	3
BIOACT® EC-7R™ Terpene Cleaner	1	1	2
Deionized Water	1	1	1
3% Alconox® Detergent	1	1	1
10% Sodium Hydroxide Solution	1	1	1
10% Sulfuric Acid Solution	2	1	1

Rating scale:

1= no visible effect

2= slight smear, bleed or print removal

3= moderate smear, bleed or print removal (print still legible)

4= severe smear, bleed or print removal (print illegible or just barely legible)

5= complete print and/or topcoat removal

NP= print removed prior to rub

**Shelf Life:** Five years when stored in its original packaging in an environment below 80°F (27°C) and 80%RH.

**Trademarks:**

Alconox® is a registered trademark of Alconox Co.

BradyTag® is a registered trademark of Brady Worldwide, Inc.

BIOACT® is a registered trademark of Petroferm, Inc.

EC-7R™ is a trademark of Petroferm Inc.

Nomex® is a registered trademark of Du Pont de Nemours, E.I. and Company

Skydrol® is a registered trademark of the Monsanto Company

Sunlighter™ is a trademark of the Monsanto Company

Super Agitene® is a registered trademark of Graymills Company

ASTM: American Society for Testing and Materials (U.S.A.)

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units

**Note:** All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

## **WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 Brady Worldwide, Inc. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission

Brady North America | 6555 W. Good Hope Road | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289