Put-Ups



Complies to HL1 & HL2 According to the Railway Standard DIN EN 45545-2

VW-1, FAR 25

- Easy, Cost And Labor Effective Wraparound Installation
- More Flexible Than Spiral Wrap Of Split Convoluted Tubing

25% Edge Overlap

Resists Chemicals & Solvents



Material PET

Grade F6F

Monofilament Diameter .008" - .015"

Drawing Number TF001F6F-WD



800.323.5140 • 973.300.9242 • fax: 973.300.9409 104 Demarest Road • Sparta, NJ 07871

Nominal Size	Part #	Wall Thickness	Monofilament Diameter	Bulk Box	Box A	Box B	Available Colors	Lbs/ 100'
1/8″	F6F0.13TB	.024″	.008″	10,000′	400′	100′	TB	0.47
1/4″	F6F0.25TB	.025″	.010″	3,000′	200′	100′	TB	0.60
3/8″	F6F0.38TB	.025″	.010″	1,200′	150′	75′	TB	1.20
1/2″	F6F0.50TB	.025″	.010″	800′	150′	75′	TB	1.40
3/4″	F6F0.75TB	.025″	.010″	500′	100′	50′	TB	1.60
1″	F6F1.00TB	.038″	.015″	400′	100′	50′	TB	2.00
1 1/4″	F6F1.25TB	.038″	.015″	250′	75′	25′	TB	2.40
1 1/2″	F6F1.50TB	.038″	.015″	200′	75′	25′	TB	2.70
2″	F6F2.00TB	.038″	.015″	150′	50′	25′	TB	3.60

Flexible, Semi-Rigid Split Sleeving Will Not Support Combustion

Flame spread is a vital safety consideration in applications as diverse as home built aircraft wiring and safely managing sound & lighting cables at clubs, concerts and theaters.

To accommodate these issues, and to provide unequaled flexibility and access, we've developed this unique sleeving product.

Self-extinguishing F6F fully complies with UL standard VW-1. The addition of a flame inhibitor to our triaxially braided F6 split sleeving provides the perfect solution to a wide range of cable management needs.

Easy slip over installation, complete access along the entire run, economy, durability and UL certified flame retardant make F6F ideal when the goal is to manage wires and cables safely and effectively.


FAR-25

The large overlap allows easy installation over splices and incline connectors without exposing wires and cables.



ABVC









700

600

500



Rating

Abrasion Resistance High

Abrasion Test Machine Taber 5150

Abrasion Test Wheel Calibrase H-18

Abrasion Test Load **500g**

Room Temperature 70°F

Humidity 63%

Slight Scuffing Visible 500 Test Cycles

Visible Wear And Five Broken Filaments 1,200 Test Cycles

Material Destroyed 1,600 Test Cycles

Pre-Test Weight 3,469.8 mg

Post-Test Weight 3,114.0 mg

Test End Loss Of Mass Point Of Destruction 355.8 mg



1=No Effect 4=More Affected 2=Little Effec 5=Severely Affected 3=Affected

Aromatic Solvents	2
Aliphatic Solvents	1
Chlorinated Solvents	3
Weak Bases	1
Salts	
Strong Bases	
Salt Water 0-S-1926	1
Hydraulic Fluid <i>MIL-H-5606</i>	
Lube Oil <i>MIL-L-7808</i>	1
De-Icing Fluid <i>MIL-A-8243</i>	1
Strong Acids	3
Strong Oxidants	2
Esters/Ketones	1
UV Light	1
Petroleum	1
Fungus ASTM G-21	1
Halogen Free	Yes
RoHS	
SVHC	

Melt Point ASTM D-2117 446°F (230°C)—

Maximum Continuous Mil-I-23053— 257°F (125°C)

VW-1

Minimum Continuous -94°F (-70°C)

400° - 40

www.techflex.com

TURES

O PHYSICAL PROPERTIES

Monofilament Diameter008"015" ASTM D-204
Flammability Rating VW-1 FMVSS-302 Approved
Recommended CuttingScissor/HK
Colors 1
Wall Thickness024"038"
Tensile Strength (Yarn4-6.5 ASTM D-2256 Lbs
Specific Gravity ASTM D-792 1.38
Moisture Absorption %12 ASTM D-570
Hard Vacuum Data ASTM E-595 at 10-5 torr
TML19
CVCM04
WVR06
ASTM E-662
OutgassingMed
Oxygen Index 31 ASTM D-2863

© 2020 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden.

Techflex® product names and logos are registered trademarks of Techflex®, unless otherwise attributed. The contents and illustritions contained herein are believed to be reliable. Techflex® makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's® only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 01-07