

- VW-1, Mil-202 Approved
- Economical And Easy To Install
- Cut And Abrasion Resistant
- Resists Gasoline And Engine Chemicals
- Hook And Loop Closure For Easy And Repeatable Access

	1 al a se a
	111
12/24	
	States All
	EUV
	HIM
	All I
and the second	THE PERSON
1991AN	and Del
ASAAA AT	
hy MAN SITE	21
	Cut Cleanly
	Cut Cleanly
	Hot Knife

Material Polyethylene Terepthalate

Grade FWF

Monofilament Diameter .010"

Drawing Number TF001FWFR-WD



		Put-Ups —					
Nominal Size	Part #	Hook & Loop Width	Recommended Application Diameter	Bulk Spool	Shop Spool	Available Colors	Lbs/ 100′
1/2″	FWF0.50TB	1/4″	0.50″	100′	20′	TB	1.30
3/4″	FWF0.75TB	5/8″	0.50″	100′	15′	ТВ	1.80
1 1/4″	FWF1.25TB	5/8″	1.00″	100′	12′	ТВ	2.30
2″	FWF2.00TB	5/8″	1.25″	100′	10′	ТВ	3.20
2 1/2″	FXF2.50TB	5/8″	-	100′	10′	ТВ	3.75

Easy On, Easy Off Access Will Not Support Combustion

Flame Retardant Flexo Wrap (FWF) provides the same hook and loop wire management flexibility as our standard Flexo Wrap along with the added safety feature of an organic flame inhibitor to provide an additional level of security.

FWF is a safe, economical solution for a wide range of cable management applications where moderate levels of flame protection are needed.



FLEXO WRAP FR is designed for quick and easy management of wire, cable and hose assemblies. Just separate the hook and loop fasteners along the edge of the material... and slip the entire length of FW around or under your harness or component assembly. The wide expandability range allows FW to easily fit around... odd-shaped connectors and gently constrict around the diameter of your wires. When the FW is in place, simply seal the hook and loop along the edges.





700

600

500°

4000

3009

200°

100

-200°.



Abrasion Resistance Medium

Rating

Abrasion Test Machine Taber 5150

Abrasion Test Wheel Calibrase H-18

Abrasion Test Load 500g

Room Temperature 70°F

Humidity 63%

Slight Scuffing And One Broken Filament 300 Test Cycles

Wear Continues Evenly Approximately One Dozen **Filaments Broken** 500 Test Cycles

Material Destroyed 900 Test Cycles

Pre-Test Weight 3,772.7 mg

Post-Test Weight 3,391.1 mg

Test End Loss Of Mass Point Of Destruction 381.6 mg



1=No Effect 2=Little Effect 3=Affected

4=More Affected 5=Severely Affected

VW-1

Aromatic Solvents	2
Aliphatic Solvents	1
Chlorinated Solvents	3
Weak Bases	1
Salts	1
Strong Bases	
Salt Water 0-S-1926	1
Hydraulic Fluid <i>MIL-H-5606</i>	1
Lube Oil <i>MIL-L-7808</i>	1
De-Icing Fluid MIL-A-8243	
Strong Acids	3
Strong Oxidants	2
Esters/Ketones	2
UV Light	1
Petroleum	1
Fungus ASTM G-21	1
Halogen Free	Yes
RoHS	Yes
SVHC	_ None

ASTM D-2117 482°F (250°C) **Maximum Continuous** Mil-I-23053 257°F (125°C)

Melt Point

Minimum Continuous -94°F (-70°C)

www.techflex.com

TEMPERATURES

ERATING

OP

PHYSICAL PROPERTIES

Monofilament Diameter ASTM D-204	.010″
Flammability Rating FMVSS-302 Approved	VW-1
Recommended CuttingHot	Knife
Colors	1
Wall Thickness	.025″
Tensile Strength (Yarn) ASTM D-2256 Lbs	5
Specific Gravity ASTM D-792	_1.38
Moisture Absorption % ASTM D-570	12
Hard Vacuum Data ASTM E-595 at 10-5 torr	
TML	19
CVCM	04
WVR	06
Smoke D-Max <i>ASTM E-662</i>	_ 275
Outgassing	Med
Oxygen Index ASTM D-2863	31

© 2020 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden.

Techflex[®] product names and logos are registered trademarks of Techflex[®], unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex[®] makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex'[®] only obligations are those in standard terms of sale for these products and Techflex[®] will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 01-07 Users should make their own evaluation to determine the suitability of these products for their unique and specific applications.