

- Easy To Install Cuts With Scissors
- Resists Damage from UV, Gasoline & Engine Chemicals
- Weld Splatter, Hot Slag, & Welding Spark Protection
- Stays Flexible In Low Temps



Material Fiberglass

Grade WWN

Wall Thickness .04″

				- Tut	ops		
Nominal Size	Part #	Wall Thickness	Velcro Width	Bulk Spool	Shop Spool	Available Colors	Lbs/ 100′
1″	WWN1.00BK	.04″	0.84″	150′	50′	Black BK	8.4
1 1/2″	WWN1.50BK	.04″	0.84″	150′	50′	Black BK	11.0
2″	WWN2.00BK	.04″	1.55″	150′	50′	Black BK	13.8
2 3/8″	WWN2.38BK	.04″	1.55″	150′	50′	Black BK	14.8
2 3/4″	WWN2.75BK	.04″	1.55″	150′	50′	Black BK	16.4
3″	WWN3.00BK	.04″	1.55″	150′	50′	Black BK	18.4
3 1/4″	WWN3.25BK	.04″	1.55″	150′	50′	Black BK	19.2
3 1/2″	WWN3.50BK	.04″	1.55″	150′	50′	Black BK	20.4
4″	WWN4.00BK	.04″	1.55″	150′	50′	Black BK	21.7

## - Put-Ups —

<b>Protects Vulnerable Welding Hoses From Catastrophic</b>
Failure.

Techflex WeldWrap (WW) is braided from fiberglass yarns with high temperature coating and velcro closure. Commonly used for protecting welding hoses against flame and abrasion, when dragging weld slag across the floor. This product will withstand continuous exposure to temperatures of 400°F/204.4°C, and intermittent introduction to temperatures of 750°F/399°C.

The heavy duty hook and loop closure ensures a tight seal and allows WeldWrap to be installed easily over existing assemblies. WeldWrap also provides a high level of abrasion and penetration protection to increase the useful life of any hoses exposed to rough or abrasive surfaces.

Color Available: Silver (SV)
Insumales and protects hoses and cables on welding robots and static welding stations.





## 1600 TEMPERATURES **CARASION AFLAMMABILITY** 1400 1200 1000 Abrasion Resistance Rating Non Flammable www.techflex.com **Intermitten Exposure** High 800°-750°F (399°C) Abrasion Test Machine 600°-Maximum Continuous PERATING Taber 5150 Mil-I-23053. 400°-400°F (204.4°C) Abrasion Test Wheel CHEMICAL 200°-Calibrase H-18 RESISTANCE 00 Minimum Continuous. Abrasion Test Load -40°F (-40°C) 0 -200°-500g 1=No Effect 4=More Affected PHYSICAL 2=Little Effect 5=Severely Affected **Room Temperature** 3=Affected PROPERTIES 77°F Humidity Aromatic Solvents \_\_\_\_\_ 1 Monofilament Diameter NA 70% ASTM D-204 Aliphatic Solvents\_\_\_\_\_ 1 Flammability Rating \_\_\_ Non Flammable Material Destroyed -Chlorinated Solvents \_\_\_\_\_ 1 Two Small Holes Worn Recommended Cutting \_\_\_\_ Scissor/Shears Weak Bases 1 Through Colors \_\_\_\_\_ \_\_\_ 1 Salts 1 1,060 Test Cycles Wall Thickness .04" Strong Bases \_\_\_\_\_ 1 **Pre-Test Weight** Salt Water 0-S-1926\_\_\_\_\_1 7,857.40 mg Hydraulic Fluid MIL-H-5606 \_\_\_\_\_ 1 Post-Test Weight Lube Oil *MIL-L-7808* 1 6,602.20 mg De-Icing Fluid MIL-A-8243 \_\_\_\_\_ 1 Test End Loss Of Mass Strong Acids \_\_\_\_\_ 2 Point Of Destruction Strong Oxidants \_\_\_\_\_ 2 1,255.20 mg Esters/Ketones \_\_\_\_\_ 1 UV Light \_\_\_\_\_ 1 Petroleum \_\_\_\_\_ 1 Fungus ASTM G-21 \_\_\_\_\_ 1

© 2020 Techflex® - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex® is strictly forbidden.

Techflex<sup>®</sup> product names and logos are registered trademarks of Techflex<sup>®</sup>, unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex<sup>®</sup> makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's<sup>®</sup> only obligations are those in standard terms of sale for these products and Techflex<sup>®</sup> will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 01-08