tyco

Electronics

High-Shrink-Ratio, Flame-Retardant, **Polyolefin Tubing**

Product Facts

- 4:1 shrink ratio
- Conforms well to highly variable substrate dimensions
- Has excellent physical, chemical, and electrical properties that meet or exceed industrial and military standards
- Shows no significant degradation when exposed to common solvents and chemicals, including aviation fuel and hydraulic fluid













Applications

Ideal for repairing harnesses or cables; will pass over a large-diameter connector or transition, and then shrink down onto a smaller-diameter jacket. Can insulate or protect a substrate of varying dimensions. Also provides the abrasion and fluid resistance required in harnessing applications.

Single Wall Tubing

RP-4800

Installation

Minimum shrink temperature: 95°C [203°F] Minimum full recovery temperature: 121°C [250°F]

Operating Temperature Range

-55°C to 135°C [-67°F to 275°F]

Specifications/Approvals

| Series | UL .511 | Military | Industry | Raychem |
|---------|---------------------------------------|-------------------------------------------------------------------|-------------------------|---------|
| RP-4800 | E35586 600V, 125°C (black only) | AMS-DTL-23053/5*, Class 1 Overexpanded VG 95343 Pt 5 Type A | VDE 0341 Pt 9005 Type A | RT-1122 |

^{*}Formerly MIL-I-23053/5 and MIL-DTL-23053/5.

| Available in: | Americas | Europe | Asia Pacific |
|---------------|----------|--------|--------------|
| | | • | • |

www.tycoelectronics.com



Electronics

Product Dimensions

Single Wall Tubing

No. 11

Raychem

1.14 ± 0.18 [0.045 ± 0.007]

RP-4800 (Continued)

| | Inside [| Recovered Wall | | |
|--------|------------------------------|------------------------------------|------------------------------|--|
| Size | Minimum Expanded as Supplied | Maximum Recovered After Heating | Thickness** After Heating | |
| No. 1 | 25.4 [1.000] | 7.0 [0.275] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 2 | 50.8 [2.000] | 14.0 [0.550] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 3 | 76.2 [3.000] | 20.6 [0.810] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 4 | 101.6 [4.000] | 26.7 [1.050] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 5 | 25.4 [1.000] | 11.7 [0.462] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 6 | 60.3 [2.375] | 17.3 [0.680] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 7 | 76.2 [3.000] | 21.3 [0.840] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 8 | 95.3 [3.750] | 23.6 [0.930] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 9 | 114.3 [4.500] | 36.8 [1.450] | 1.14 ± 0.18 [0.045 ± 0.007] | |
| No. 10 | 38.1 [1.500] | 9.5 [0.375] | 1.14 ± 0.18 [0.045 ± 0.007] | |

4.6 [0.180]

Ordering Information

| Color | Standard | Black (-0) | |
|-------------------------|---------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------|--|
| | Nonstandard | White (-9), red (-2), blue (-6), yellow (-4), green (-5), brown (-1), orange (-3), violet (-7), gray (-8) | |
| Size selection | On Always order the largest size that will shrink snugly over the component to be covered. Special order sizes are available upon request. | | |
| Standard packaging | On spools or in 1.2-meter [4-foot] lengths. | | |
| Ordering description*** | Specify product name, size and color (for example, RP-4800 NO.1-0). | | |

^{***}Europe only. For supply to MIL, Def Stan and BS add -MS, -DS or -BS to ordering description.

^{19.1 [0.750]} **Wall thickness will be less if tubing recovery is restricted during shrinkage.